

Page number: 01



Composition Mixture of pigments, fillers and anticorrosive pigments in solution of alkyduretan resin in organic solvent with addition of driers and additives.

Characteristics and use The paint is determined for anticorrosive single coats of steel objects for aggressive, corrosive environment C1-C3, i.e. municipal and industrial atmosphere with moderate pollution with sulphur dioxide. The paint film has silky semi-gloss surface.

- ◆ excellent adhesion to steel surfaces
- ◆ quick drying
- ◆ suitable for the tinting system HOSTEMIX
- ◆ increased resistance to water absorption
- ◆ paint 2in1 for cost-saving work
- ◆ suitable for indirect food contact

Application area Exterior and interior with medium corrosive stress (laundry rooms, cellars, industrial areas, workshops), transport containers, metal plate and steel constructions, fencing, metal sheet garages, gates, small metal objects.

Shades According to BALT, RAL, NCS and ČSN colour chart and the others according to individual customer requirements.

Physical properties	Flow time	110 - 130 s (cup Ford Ø 6 mm)
	Weight solids	> 72 % according to shade
	Volume solids	47 - 50 %
	Flash point	>25 °C
	Density	1500 - 1650 kg/m ³

Emission limits	VOC: 0.30 – 0.34 kg/kg	TOC: 0.24 – 0.28 kg/kg
	This product is for professional use only. Not for DIY.	

Properties of dried coat	Hiding power	degree 1 - 2
	Gloss / 60°	10 - 30
	Hardness /Persoz/	up 8 % after 24 h
	Adhesion with crosshatch test	degree 0

Drying time	Surface temperature	10 °C	15 °C	23 °C	23 °C
	Dust free	45 min	45 min	45 min	60 min
	Dry through	24 h	20 h	16 h	24 h
	Dry film thickness DFT	40 µm	40 µm	40 µm	80 µm

Spreading capacity	Wet film thickness WFT	80 - 85 µm	160 - 180 µm	240 - 255 µm
	Dry film thickness DFT	40 µm	80 µm	120 µm
	Theoretical spreading capacity	7.5 – 8.5 m ² /kg	3.8 – 4.2 m ² /kg	2.5 – 2.8 m ² /kg

Thinning TELSOL BR 5, TELSOL BR 6, BALTECH S6005, BALTECH S6006

Surface preparation For corrosive environment C2 and C3 the surface must be prepared by blast-cleaning to degree Sa 2 ½ according to EN ISO 8501-1 (welds and edges must be prepared according to EN ISO 8501-3). For corrosive environment C1 the surface must be clean, dry, free of grease and rust, mechanically cleaned to degree St 2 – St 3.
It is necessary to clean, degrease and remove poorly adhering old coats from previously painted surfaces. To ensure compatibility of new coat with old one it is recommended to contact the producer or carry out test reference coating on surface of 1 m².

Page number: 02



Application conditions

Stir the paint properly with a mechanical stirrer before use so that there will be no sediment on the bottom. To thin and filter if it necessary.

The temperature of the paint itself should be 15-25 °C. If the paint temperature is below 15 °C, a higher dilution is required and this can subsequently cause problems with the formation of a homogeneous paint film and a longer drying time.

For coating / spraying outside the suitable weather forecast is necessary. During rain, fog, creation of condensation water, effect of aggressive gases and during wind with strong content of dust the coating work must be suspended and can be restart after absolute drying of surface-treated material. Minimal air temperature for application is 10 °C, temperature of painted surface must be 3 °C above dew point. Temperature and relative humidity must be measured in proximity of painted surface. The surface temperature must not be higher than 40 °C. Relative humidity must not be higher than 75 %. Lower temperature and higher humidity during an application and a drying and high thickness of applied coats markedly slow down drying and hardening of the coat. Imperfectly dried surface can cause problems with adhesion of paint to surface or with adhesion between individual coats. In addition it can negatively affect overall appearance of the paint film.

Do not apply the paint on a hot summer day.

Stackability must be tested for specific conditions (climatic conditions, thickness, number of coats, the shape of the substrate, substrate type, etc.).

Workflow

Apply 2 to 3 coats (spraying) of TELKYD S200 E, final dry film thickness should be at least 80 µm. In cases, where it is necessary, recoating is possible by the system so-called "wet into wet" or after less than 8 hours.

The paint is applied by cross spraying or in parallel strips to achieve a final uniform layer. First it is necessary to treat problematic places (corners, edges, welds, surface defects).

It is very important to apply each coat in a uniform layer, in a thickness specified by the specific paint system. Consumption of paint must be checked to avoid excessive thickness, to avoid splashing, cracking and solvent retention.

For larger compact areas always use the material from the same batch. Using the same batch can guarantee the same shade of the colour. We recommend to mix the content of the individual cans by homogeneous mixing.

Optimal thickness of system

The optimal thickness and composition of the paint system depends on the aggressivity of atmosphere and on the expected durability of a protective system. The selection of an appropriate system should be in accordance with EN ISO 12944-5: 2018.

Application

Airless/AirMix spraying (5-15 % thinning depending on the type of device)

Conventional spraying (recommended viscosity 25 – 35 s / cup Ford Ø 4 mm; 20 - 25 % thinning)

Brush (recommended viscosity 60 - 80 s / cup Ford Ø 4 mm; 10 - 15 % thinning)

Roller (velour) (recommended viscosity 50 - 80 s / cup Ford Ø 4 mm; 10 - 15 % thinning)

Application by brush and by roller is recommended only for small areas and for corrections.

Application data

Data for conventional spraying

Spraying gun e.g. EST 115, EcoGun 116, EcoGun 246

Nozzle according to desired capacity 1.4-2.0; Air pressure 2.5 – 3 atm

Data for airless spraying Airless/AirMix (tested on the device EcoPump VP 55 445, 64:1 gear ratio, in combination with air assist spraying gun EcoGun 2100 (DÜRR))

Device	Nozzle	Pressure on nozzle	Thinning
AirMix	0.011 inch (0.28 mm)	12-17 Mpa (120-170 atm) air assist 1.5-2.5 atm	5-15 %
AirMix	0.013 inch (0.33 mm)	15-20 Mpa (150-200 atm) air assist 1.5-2.5 atm	5-10 %
Airless	0.011 inch (0.28 mm)	15-20 Mpa (150-200 atm)	5-10 %

Page number: 03



Airless	0.013 inch (0.33 mm)	17-25 Mpa (170-250 atm)	5 %
---------	----------------------	-------------------------	-----

Recommended filter of spraying gun yellow 100/149 (mesh/ μm), spraying angel 20 – 60°. It is not recommended using free adjustable nozzle.

Handling

Read the instructions in the Safety Data Sheet before use and follow all safety instructions and regulations. The product contains organic solvents. Follow basic hygiene rules. Do not eat, drink or smoke while using this product. Avoid contact with eyes, skin or clothing. Wear protective gloves, eye protection, protective clothing. Ensure effective ventilation of the workplace.

Packing

10 kg; 20 kg; 25 kg (tinted product)

Storability

The product keeps the product qualities 5 years from production date in original closed container. To store in dry storage at the temperature 5 to 25 °C. Flammable liquid II. hazard class.

Disposal of packing and waste

Hand over the used, properly empty packing at the collection point of the packing waste. Dispose the packing with the product rest at the place determined by the town for disposal of hazardous waste or hand over to the person authorized for hazardous waste disposal. Further see the product safety data sheet.

These data are only for information and their accuracy is influenced by the properties of individual materials and unpredictable factors during application. The user is responsible for correct use of the product according to the direction for use and for correct application of painting system, i.e. he must always evaluate all conditions of application, which could influence final quality of the top treatment. Therefore we always recommend to the user to carry out the test for actual working conditions and type of surface applied. Above mentioned data are data, which influence individual working conditions and therefore they do not establish a legal claim. It is necessary to consult information outside the terms of this catalogue sheet with the producer.

The producer stipulates the right for the change in the catalogue sheets without previous notification.